

PALISADE SA-HT

SELF-ADHERED UNDERLAYMENT

DESCRIPTION

PALISADE SA-HT is a high temperature stable (250°F) self-adhered underlayment for steep slope applications and provides full roof deck waterproof protection. **PALISADE SA-HT** is engineered to provide the most advanced all weather high traction walking surface in the marketplace featuring **STRONGHOLD™** a patented top surface featuring a unique pattern of polymer dots and a grip enhanced back side coating.

PRODUCT SPECIFICATIONS

Facer: Woven, clear PP scrim with specialized, non-woven top surface
Color: Blue/Blue
Weight: 45 lb per roll
Thickness: 40 mil (ASTM D1777)

ROLL SPECIFICATIONS

Cores: 2.5" (63.5 mm)
Width: 36" (91.4 cm)
Length: 66.7'/roll (20.3 m)
Coverage: 200 sq ft (18.6 m²)

These values are typical data and are not intended as limiting specifications.



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA
Customer Service: 800.565.2000
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 07/24

INTERTAPE POLYMER GROUP

TECHNICAL DATA SHEET

PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. These data should not be considered specification.

Release Liner	Silicone treated split-release liner
Permeability ASTM E96	<0.01 perms
Nominal Thickness ASTM D1777	>40 mil
Nail Sealability ASTM D1970	Pass
Lap Sealability ASTM D1970	Pass
Tensile Strength ASTM D226	121 lbf/in
Tear Strength ASTM D4523	160 lbf/in
Elongation ASTM D2523	16%
Low Temperature Flexibility ASTM D1970	Pass
Adhesion to Plywood - 75°F ASTM D1971	55 lbf/ft
Adhesion to Plywood - 40°F ASTM D1971	12 lbf/ft
Thermal Stability ASTM D1970	250°F

- Meets ASTM D1970
- Meets ICC-ES AC 188 **CCRR-1105**
- Florida Building Code Approved **FL5325**
- Miami-Dade County Product Control Approved
- Texas Department of Insurance
- Up to 6 months UV Exposure
- Lifetime Limited Warranty